GRS-7045-2507E

## THERMONIX GREASE EP

### **High-Temperature Grease**

**THERMONIX GREASE EP** is made from a clay thickener (Bentonite) and highly refined mineral base oils, which possesses outstanding mechanical stability and resistance to heat and water. **THERMONIX GREASE EP** also contains molybdenum disulphide for added anti-wear protection.

#### Special Features

#### 1. Excellent heat resistance

**THERMONIX GREASE EP** is used for the lubrication of various machines that are exposed to high temperature such as dryer blowers. However, under the high temperatures more than 180°C, it is necessary to push old grease and to supply new grease regularly.

- 2. Outstanding extreme-pressure, anti-wear and adhesive properties
- 3. Good water resistance and pressure resistance
- **4.** Usage in a wide temperature range THERMONIX GREASE EP can be used in a very wide temperature range, from -20°C to 200°C, and has the outstanding lubricity also at low temperature and high temperature.

#### Applications

**THERMONIX GREASE EP** can be used on lubrication points of various machines that are exposed to high temperature.

#### Containers

180-kg drum, 16-kg pail can

Typical Properties of THERMONIX GREASE EP

Grade				1	2
Thickener				Bentonite	Bentonite
Appearance	2			Dark gray, Buttery	Dark gray, Buttery
Base oil	Type			Mineral oil	Mineral oil
	Kinematic viscosity	(100°C)	$mm^2/s$	31.3	30.7
Penetration		$(25^{\circ}\text{C}, 60\text{W})$		323	282
Worked stability		(25°C, 100,000W)		335	296
Dropping point			°C	None	None
Oil separation		$(100^{\circ}\text{C}, 24 \text{ h})$	mass%	1.7	1.0
Evaporation loss		(99°C, 22 h)	mass%	0.05	0.08
Oxidation stability		(99°C, 100 h)	kPa	28	24
Copper strip corrosion		$(100^{\circ}\text{C}, 24 \text{ h})$		No change	No change
Four-ball test		Weld load(200r/min)	MPa	1.8	1.8
Approx. operating temperature range			°C	-20 to 200	-20 to 200

Note: The typical properties may be changed without notice. (July 2025)



# Handling **Precautions**

#### lacksquare Follow these precautions when handling this product.

Composition :	Mixtures (Base Oil(s), Thickener, Additives)			
Hazard category:	Not applicable			
Precautionary statements:	· Do not handle until all safety precautions have been read and understood.			
	Wear protective gloves/protective clothing/eye protection/face protection.			
Prevention	• Do not allow the eyes to become exposed to the product. Do not swallow the product.			
	Wash hands thoroughly after handling.			
	• Do not eat, drink or smoke when using this product.			
Response	esponse • IF SWALLOWED: Immediately call a POISON CENTER/doctor.			
	IF SWALLOWED: Rinse mouth. Do NOT induce vomiting.			
	• If the eyes are exposed to the product: Rinse the eyes with plenty of running water and			
	immediately contact a physician.			
	• IF ON SKIN: Wash with plenty of soap and water.			
Storage	The product must be stored in a cool, well-ventilated location where it will not be exposed			
	to direct sunlight.			
	Containers that have been opened must be tightly sealed.			
Disposal	Dispose of contents/container in accordance with local/regional/national/international			
	regulations.			
	If there are any doubts about proper methods of handling the product, contact the point of			
	purchase before proceeding with usage.			