1-1-2 Otemachi, Chiyoda-ku, Tokyo 100-8162, Japan

IND-5542-2104E

## **ANTIRUST TERAMI LS-S**

# Barium-free long-term solvent-diluting rust preventive oil

ANTIRUST TERAMI LS-S is a long-term solvent-diluting rust preventive oil which has been newly developed based on research and improvements over the years. ANTIRUST TERAMI LS-S is not sticky because petrolatum is not contained and it is excellent in the working efficiency. ANTIRUST TERAMI LS-S is safe to use for rust prevention applications of various mechanical parts since barium type additives are not contained. ANTIRUST TERAMI LS-S has a lower viscosity compared with conventional long-term rust preventive oil, so it can realize efficiency in coating work and reduce take-out amount.

#### SPECIAL FEATURES

#### 1. Excellent Rust Prevention

ANTIRUST TERAMI LS-S is formulated with carefully selected mineral oil and rust-preventive additives. After the solvent has evaporated, ANTIRUST TERAMI LS-S forms a thin and non drying coating that provides excellent long-term protection from rust.

#### 2. Good for the Ecology

**ANTIRUST TERAMI LS-S** is an environmentally-friendly product due to barium-free type and high boiling point solvent is used.

#### 3. Low Risk of Fire

**ANTIRUST TERAMI LS-S** has a high flash point although it contains solvents. So it can be used with low risk of fire.

#### 4. Good Removal

Film of **ANTIRUST TERAMI LS-S** is easily removed with a petroleum solvent or alkaline process cleaner.

#### 5. Easy to Use

ANTIRUST TERAMI LS-S is not sticky because petrolatum is not contained and has a lower viscosity. Thus it makes working efficiency excellent. Moreover, it is easy to pass through a filter. In result, quantity of take-out amount will be decreased.

#### APPLICATIONS

Machine parts, precision machine parts, etc.

#### COATING METHOD

Immersion, spraying, brushing

#### CONTAINERS

200-liter drums and 20-liter cans

### Typical Properties of ANTIRUST TERAMI

#### LS-S

(ASTM)		L3.5
(15°C)	g/cm <sup>3</sup>	0.825
(40°C)	$mm^2/s$	3.8
(PM)	°C	84
ement (JIS K2246 6.29)		Pass
(JIS K2246	5 NP-3)	Pass
(Class A h	olding	> 1,000
time)	h	
(Class A holding		> 24
time)	h	
(Indoors)	months	6
		Non drying
		and
		transpar-
		ent film
(Approx.)	μm	2~3
	(15°C) (40°C) (PM) (JIS K2246 (JIS K2246 (Class A he time) (Class A he time) (Indoors)	(15°C) g/cm³ (40°C) mm²/s (PM) °C (JIS K2246 6.29) (JIS K2246 NP-3)  (Class A holding time) h (Class A holding time) h (Indoors) months

Note: The typical properties may be changed without notice (September 2018).



# Handling **Precautions**

### lacksquare Follow these precautions when handling this product.

Composition:	Base Oil, Additives
Precautionary pictograms:	
Signal word:	Danger
Hazard Statement:	Combustible liquid
	May be fatal if swallowed and enters airways
Precautionary Statements:	• Do not handle until all safety precautions have been read and understood.
Prevention	• Wear protective gloves/protective clothing/eye protection/face protection.
	• Do not allow the eyes to become exposed to the product. Do not swallow the product.
	• Keep away from heat/sparks/open flames/hot surfaces – No smoking.
	Use explosion-proof electrical/ventilating/lighting/equipment.
	Ground/bond container and receiving equipment.
	Wash hands thoroughly after handling.
	• Do not eat, drink or smoke when using this product.
Response	• IF SWALLOWED: Immediately call a POISON CENTER or doctor/physician.
	• IF SWALLOWED: Rinse mouth. Do NOT induce vomiting.
	• If the eyes are exposed to the product: Rinse the eyes with plenty of running water and
	immediately contact a physician.
	• IF ON SKIN: Wash with plenty of soap and water.
	• Do NOT induce vomiting.
	• In case of fire: Use suitable extinguishing media for extinction.
Storage	• The product must be stored in a cool, well-ventilated location where it will not be exposed
	to direct sunlight.
	Containers that have been opened must be tightly sealed.
	• Store in a well ventilated place. Keep cool.
	Store locked up.
Disposal	Dispose of contents/container in accordance with local/regional/national/international
	regulations.
	• If there are any doubts about proper methods of handling the product, contact the point of
	purchase before proceeding with usage.